

# National Bureau of Standards Certificate of Analysis

## Standard Reference Material 692 Iron Ore (Labrador)

(In Cooperation with the American Society for Testing and Materials)

This material is in the form of powder (<0.1mm) for use in checking chemical methods of analysis and in calibration with instrumental methods of analysis.

(Results based on samples dried for one hour at 105 °C.)

Constituent	Total Fe	SiO <sub>2</sub>	Al <sub>2</sub> O <sub>3</sub>	P	S	TiO <sub>2</sub>	MnO	CaO	MgO	Na <sub>2</sub> O	K <sub>2</sub> O
Certified <sup>1</sup> Value (wt. %)	59.58	10.14	1.41	0.039	0.005	0.045	0.46	0.023	0.035	0.008	0.039
Estimated <sup>2</sup> Uncertainty	0.06	0.05	0.04	0.002	0.001	0.005	0.01	0.003	0.004	0.002	0.003
Method <sup>3</sup>											
Labs	SnCl <sub>2</sub> - K <sub>2</sub> Cr <sub>2</sub> O <sub>7</sub>	HClO <sub>4</sub> Dehydration	Atomic Absorption	Photometric	Combustion- Titration	Photometric	Atomic Absorption	Atomic Absorption	Atomic Absorption	Atomic Absorption	Atomic Absorption
A	<sup>a</sup> 59.55	<sup>b</sup> 10.09	1.40	<sup>c</sup> 0.039	<0.005	<sup>d</sup> 0.041	0.47	0.022	0.034	0.008	0.040
B	59.58	10.26	1.48	<sup>c</sup> .035	.004	<sup>e</sup> .05	.45	.02	.04	.005	.036
C	<sup>f</sup> 59.63 59.62	10.10	1.42	.040	.007	<sup>g</sup> .048	<sup>h</sup> .47	<sup>i</sup> .025	<sup>i</sup> .028	<sup>i</sup> .008	<sup>j</sup> .040 <sup>i</sup> .039
D	59.60	10.16	1.40	-	-	<sup>j</sup> .043	.47	<sup>j</sup> .021	.033	<sup>j</sup> .010 .009	<sup>j</sup> .041
E	59.50	<sup>h</sup> 10.12 10.05	<sup>k</sup> 1.41	.039	.004	<sup>g</sup> .050	.46	.01	.038	.008	.041
F	59.58	10.18	<sup>l</sup> 1.37 1.46	.040	.005	<sup>g</sup> .043	<sup>h</sup> .46	.026	.035	.008	.035

1. The certified value listed for a constituent is the *present best estimate* of the "true" value based on results of the cooperative analytical program for certification.
2. The estimated uncertainty is based on judgment and represents an evaluation of the combined effects of method imprecision, possible systematic errors among methods, and material variability for samples of 0.5 g or more. (No attempt was made to derive exact statistical measures of imprecision because several methods were involved in the determinations.)
3. A detailed description of many of the methods of analysis employed in the certification program for this SRM may be found in Part 12, Chemical Analysis of Metals and Metal Bearing Ores, Annual Book of ASTM Standards.

- a H<sub>2</sub>S reduction
- b Sample fused in Na<sub>2</sub>CO<sub>3</sub>
- c Alkali-molybdate method
- d H<sub>2</sub>O<sub>2</sub> photometric
- e Atomic absorption
- f Silver reductor

- g Chromotropic acid photometric
- h Photometric method
- i Spectroscopic method
- j Flame emission
- k Chromazurol S photometric
- l Mercury cathode-NH<sub>4</sub>OH-Cupferron-AlPO<sub>4</sub>

Washington, D.C. 20234  
 October 24, 1978

J. Paul Cali, Chief  
 Office of Standard Reference Materials

(over)

#### PLANNING, PREPARATION, TESTING, ANALYSIS:

The iron ore material for this SRM was prepared in final powder form, minus 74  $\mu\text{m}$  (200 mesh), by the Bethlehem Steel Corporation, Bethlehem, Pa. through the courtesy of J. M. Karpinski.

At NBS, the material was resieved and thoroughly blended.

Homogeneity testing of selected samples representative of the final lot was performed at NBS by R. K. Bell, Assistant Research Associate, ASTM-NBS Research Associate Program. The results for iron indicate that the material variability (0.5 g samples) is  $\leq$  the method imprecision.

Chemical analyses for certification were performed in the following laboratories:

Bethlehem Steel Corporation, Homer Research Laboratories, Bethlehem, Pa., D. A. Flinchbaugh.

Inland Steel Company, Indiana Harbor Works, East Chicago, Indiana, J. E. Joyce.

Ledoux and Company, Teaneck, New Jersey, S. Kallman and C. L. Maul.

National Bureau of Standards, Center for Analytical Chemistry, Washington, D.C., T. C. Rains, T. J. Brady, J. D. Messman, and T. A. Rush, and by R. K. Bell, ASTM Assistant Research Associate.

STELCO, The Steel Company of Canada, Ltd., Hilton Works, Hamilton, Ontario, Canada, O. P. Bhargava.

United States Steel Corporation, Research Laboratory, Monroeville, Pa., L. M. Melnick, J. D. Selvaggio, R. W. Cline, D. G. Cunningham, A. V. Fioravanti, J. R. Lucas II, C. W. Ponsonby, L. E. Povirk,

D. Shafferman and R. J. Wargo.

The overall direction and coordination of the technical measurements leading to certification were performed jointly by R. E. Michaelis, Office of Standard Reference Materials, and by J. I. Shultz, Research Associate, ASTM-NBS Research Associate Program.

The technical and support aspects involved in the preparation, certification, and issuance of this Standard Reference Material were coordinated through the Office of Standard Reference Materials by W. P. Reed.