

206.4 - Superconducting Critical Current (wire form)

This SRM is for checking the performance of measurement systems used in superconductor technology. It consists of 2.2 m of a multifilamentary niobium titanium, copper-stabilized superconducting wire wound in a single layer onto a spool with a core diameter of 8.7 cm.

PLEASE NOTE: The tables are presented to facilitate comparisons among a family of materials to help customers select the best SRM for their needs. For specific values and uncertainties, the certificate is the only official source.

SRM	Description	Unit of Issue	Critical Current (A)	Magnetic Field (T)
1457	Superconducting Critical Current - Nb Ti Wire	each	293.30, 187.38, 124.72, 69.72	2.000, 4.000, 6.000, 8.000

- Certified values are normal font
- Reference values are italicized
- Values in parentheses are for information only